

# Product Datasheet BRUX CHECKER®

## 1 Identification of the substance / preparation / company

### Product details

Trade name:	BRUX CHECKER®
Application of the substance / preparation:	Manufacture of dental pressure moulding splints.
Manufacturer / Supplier:	SCHEU DENTAL GmbH Am Burgberg 20 58642 Iserlohn Germany Tel. 0049 2374 9288-0

## 2 Composition / information on ingredients

### Chemical characterization

CAS-Number:	9002-86-2 (PVC) / 16423-68-0 (dye)
Designation:	Coated polyvinyl chloride foil (PVC)

### Coating components

Lacquer	9,10,16-Trihydroxypalmitinacid
Lacquer	Shellolacid
Dye	Dinatrium-2-(2,4,5,7-tetraiod- 6-oxido-3-oxo-xanthen-9-yl)benzoat

## 3 Handling and storage

### Handling

Information for safe handling:	When using do not eat, drink or smoke. Provide suction extractors if dust is formed.
--------------------------------	---

### Storage

Storage conditions:	Store dry and dark at max. 30°C
---------------------	---------------------------------

## 4 Physical, chemical, mechanical and biological properties

### 4.1 General properties

Properties	Guideline	Value
Form	-	Solid
Colour	-	Transparent film with a red paint layer
Odour	-	Odourless
Density	ISO 1183	1,33 g/cm <sup>3</sup>
Water absorption after 24 h at 23°C	ISO 62 Methode 1	-

# Product Datasheet BRUX CHECKER®

## 4.2 Mechanical properties

Properties	Guideline	Value
Tensile strength	ISO 527	> 42 MPa
Flectional strength	ISO 527	-
Impact strength 23°C	ISO 179	600 KJ/m <sup>2</sup>
Notched 23°C	ISO 179	-
Yield strain	ISO 527	-
Yield stress	ISO 527	-
Elasticity	DIN 53377	+/- 4%
Elongation at tear	ISO 527	-
E-modulus	ISO 527	-
Hardness Shore D	DIN 53505	~ 78

## 4.3 Thermal properties

Vicat softening point	ISO 306 / Verfahren B/50	74 °C
Thermoform resistance	ISO 75	55°C
Continuous stress temperature	ISO 75	55°C

## 4.4 Biological properties / Biocompatibility

The material has been tested on biocompatibility according to DIN EN ISO 10993.

## 5 Stability and reactivity

### Thermal decomposition / Conditions to avoid:

No decomposition by indended use.

## 6 Disposal considerations

The material can be recycled after separation or deposed of like commercial or household waste.

The aforementioned data are given most conscientiously but without any obligation. Any processing details are provided merely for guidance: it is the user's responsibility to check the suitability of the product for the intended application.